

OR 2673-224

JUN 01 2010

59724

MAY 17 2010 **NEW**
DATE REVIEWER *Dup*



ACT

with SLIME FIGHTER®

Season - to - Season Antifouling Protection
Eliminates Paint Build Up and Sanding
Slime Fighter® Improves Antifouling
Performance by Reducing Slime

KEEP OUT OF REACH OF CHILDREN
CAUTION

See Side Panel for Additional Precautionary Statements

ONE U.S. GALLON
(3.785 L)

7740b
GRAY WHITE



AkzoNobel

ACTIVE INGREDIENTS	
CUPROUS OXIDE	29.73%
N-CYCLOPROPYL-N'(1,1-DIMETHYLETHYL)-6-(METHYLTHIO)-1,3,5-TRIAZINE-2,4-DIAMINE	0.98%
INERT INGREDIENTS	69.29%
	100.00%

COPPER AS METALLIC 26.40%

EPA ESTABLISHMENT NO. 2693-NJ
EPA REGISTRATION NO. 2693-227
Contains aromatic petroleum distillates
and o-,m-,p-xylenes

DISCLAIMER: The performance of any marine coating depends on many factors outside the control of International Paint LLC including the surface preparation, proper application and the environmental conditions. Therefore, International Paint LLC cannot guarantee the suitability of this product for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use, of the product, buyer agrees that the sale and accurate remedy, if any, is limited to the return of the purchase price or replacement of the product at International Paint LLC's option.

yachtpaint.com

ACT with Slime Fighter

PRODUCT DESCRIPTION: ACT with Slime Fighter uses Ablative Technology to provide excellent season-to-season protection. Ablative Technology enables it to erode away with use and eliminates the build-up of old spent coatings and the heavy sanding needed to remove them. ACT with Slime Fighter is very effective at controlling shell fouling such as barnacles and zebra mussels and contains a Slime Fighter to control weed, slime and algae growth which helps to keep the boat bottom cleaner longer. It provides excellent protection against all forms of marine fouling in waters with moderate to heavy fouling and can be used in fresh, salt and brackish waters.

DIRECTIONS FOR USE: It is a violation of Federal law to use this product in a manner inconsistent with its labeling.

V.O.C.: Less than 400 grams/liter (3.34 lbs./gallon) **THEORETICAL COVERAGE:** 430 sq. ft./ gallon yields 2 mils dry film thickness.

THINNER: SPECIAL THINNER 216 or **DRY TIMES:** Touch dry -1 hour
BRUSH-EASE 433 **77°F (25°C)** Dry to overcoat - 12 hours minimum
Dry to launch - 12 hours minimum

THINNING: Thin only when necessary
Do not exceed 10% maximum.

CLEAN-UP: SPECIAL THINNER 216 or **APPLICATION TEMPERATURE:** 50°F (10°C)
BRUSH-EASE 433 and above (air and hull)

Temperature F (°C)	Touch Dry	Overcoating Time Minimum	Immersion Time Minimum
50°F (10°C)	3 Hours	16 Hours	16 Hours
60°F (15°C)	2 Hours	12 Hours	12 Hours
77°F (25°C)	1 Hours	12 Hours	12 Hours
95°F (35°C)	30 Minutes	8 Hours	8 Hours

*If the air temperature falls below 50°F (10°C) during the 16 hour dry time extend the dry times to 36 hours minimum.

PREPARATION

PREVIOUSLY PAINTED - GOOD CONDITION: Remove all traces of loose paint and contamination by sanding the entire surface with 80 grit sandpaper, wipe surface clean with Special Thinner 216.

PREVIOUSLY PAINTED - POOR CONDITION: Completely remove all old antifouling paint, using Interlux 299E. Sand and wipe clean with Fiberglass Solvent Wash 202.

BARE FIBERGLASS (POLYESTER OR VINYLESTER) - SURFACE PREPARATION: It is very important that bare fiberglass be properly prepared to prevent delamination of the antifouling paint. Begin by scrubbing the surface thoroughly with a stiff brush using soap and water to remove loose dirt and contamination. Flush with fresh water to remove the soap residue and allow to dry.

Remove mold release wax using one of the following Interlux products. Fiberglass Surface Prep YMA601 or Low VOC Fiberglass Surface Prep 202V following the product label instructions. To be certain that all of the contamination has been removed, run water over the surface, if the water beads up or separates, clean again. When the water sheets off, all contamination has been removed. After the surface has been properly cleaned, proceed with one of the application systems below.

APPLICATION

BARE FIBERGLASS - NO SAND SYSTEM: Clean the surface following the preparation procedure above. Repair any surface imperfections using Watertite YAV135. Sand and wipe clean. Apply one thin, continuous coat of Fiberglass No Sand Primer YPA200 by brush or roller. Follow application directions for primer and apply two coats of ACT with Slime Fighter, following dry times above.

BARE FIBERGLASS - SANDING SYSTEM: Clean the surface following the preparation procedure above. Sand the entire surface with 80-grit sandpaper and wipe clean with Fiberglass Solvent Wash 202 to remove sanding residue. Repair any surface imperfections with Watertite YAV135. Sand and wipe clean. Apply two coats of ACT with Slime Fighter following dry times above.

BARE WOOD: Sand the entire surface with 80-grit sandpaper, wipe surface clean with Interlux Special Thinner 216. Repair any imperfections with Watertite YAV135. Sand and wipe clean. Apply the first coat of ACT with Slime Fighter thinned 10% with Special Thinner 216 or Brush-Ease 433. Fill seams with Seam Compound 30 (if necessary). Then apply 2 full coats unthinned of ACT with Slime Fighter.

UNDERWATER METALS: Contact the Interlux Technical Service Department at 1-800-468-7589 for full information on how to properly prime underwater metals. **DO NOT USE ON ALUMINUM.**

APPLICATION

ACT with Slime Fighter can be applied over existing antifouling paint as long as the old coating is tightly adhered and is in sound condition. Soft antifouling paints will need to be removed or overcoated with Primocon before applying ACT with Slime Fighter.

HINTS

ACT with Slime Fighter can be applied over existing antifouling paint as long as the old coating is tightly adhered and is in sound condition. Soft antifouling paints will need to be removed or overcoated with Primocon before applying ACT with Slime Fighter.

Color difference may occur between actual paint and color swatch on front of can.

PRECAUTIONARY STATEMENTS HAZARDS TO HUMANS AND DOMESTIC ANIMALS

CAUTION

Harmful if absorbed through skin or inhaled. Causes moderate eye irritation. Avoid contact with eyes, skin or clothing. Wear protective clothing such as chemical-resistant gloves, long-sleeved cotton shirt, long pants, and hat. Wear protective eyewear (goggles, safety glasses, or face shield). Avoid breathing spray mist. While spraying paint or sanding or sand blasting boat surfaces, wear a mask or a respirator jointly approved by the Mine Safety and Health Administration (MSHA) and the National Institute of Occupational Safety & Health. Wash thoroughly with soap and water after handling. Remove contaminated clothing and wash clothing before reuse. May pose an aspiration pneumonia hazard.

FIRST AID

If on skin or clothing:

- Take off contaminated clothing.
- Rinse skin immediately with plenty of water for 15-20 minutes.
- Call a poison control center or doctor for treatment advice.

If inhaled:

- Move person to fresh air.
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible.
- Call a poison control center or doctor for further treatment advice.

If in eyes:

- Hold eyes open and rinse slowly and gently with water for 15-20 minutes.
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye.
- Call a poison control center or doctor for treatment advice.

If swallowed:

- Call a poison control center or doctor immediately for treatment advice.
- Do not give any liquid to the person.
- Do not induce vomiting unless told to do so by a poison control center or doctor.
- Do not give anything by mouth to an unconscious person.

Other: Have the product container or label with you when calling a poison control center or doctor or going for treatment.

ENVIRONMENTAL HAZARD:

This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans and other waters unless in accordance with the requirements of a National Pollutant Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent to sewer system without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

PHYSICAL OR CHEMICAL HAZARD: Flammable. Keep away from heat and open flame.

STORAGE AND DISPOSAL

Do not contaminate water, food or feed by storage or disposal. Open dumping is prohibited.

PESTICIDE STORAGE: Store in a cool, dry place.

PESTICIDE DISPOSAL: Pesticide wastes are acutely hazardous. Improper disposal of excess pesticide, spray mixture, or rinsate is a violation of Federal Law. If these wastes cannot be disposed of by use according to label instructions, contact your State Pesticide or Environmental Control Agency, or the Hazardous Waste representative at the nearest EPA Regional Office for guidance.

CONTAINER DISPOSAL: Nonrefillable container. Do not reuse or refill this container. Triple rinse as follows: Empty the remaining contents into application equipment or a mix tank and drain for 10 seconds after the flow begins to drip. Fill the container 1/4 full with water and recap. Shake for 10 seconds. Pour rinsate into application equipment or a mix tank or store rinsate for later use or disposal. Drain for 10 seconds after the flow begins to drip. Repeat this procedure two more times.

FOR CHEMICAL EMERGENCY, SPILL, LEAK, EXPOSURE OR ACCIDENT, CALL TOLL FREE: CHEMTREC 1-800-424-9300 (DAY OR NIGHT) MEDICAL ADVISORY: CONTACT YOUR LOCAL POISON CONTROL CENTER OR CALL 1-800-854-6813.

Label Rev. 021209

Interlux, 'Slime Fighters' and 'Interlux' are registered trademarks of Akzo Nobel.

Interlux.

International Paint LLC.
2270 Morris Ave., Union, NJ 07083 • 908-686-1300



ZEE128qa Label Rev. 021209